

RECOMMENDED CUTTING CONDITIONS

Workpiece Material	Structural Steel SS Carbon Steel S-C (−25HRC)		Alloy Steel SCM Tool Steel SK (−35HRC)		Alloy Steel SCM Die Steel SKD (−40HRC)		Cast Iron FC	
	Dia. DC (mm)	Revolution (min ^{−1})	Feed rate (mm/rev)	Revolution (min ^{−1})	Feed rate (mm/rev)	Revolution (min ^{−1})	Feed rate (mm/rev)	Revolution (min ^{−1})
0.5	8000	0.01	7000	0.008	6000	0.005	8000	0.01
1.0	6000	0.02	5500	0.01	4500	0.008	6000	0.02
2.0	4700	0.05	3600	0.03	2400	0.02	4700	0.05
3.0	3200	0.10	2400	0.08	1800	0.05	3500	0.10
6.0	1600	0.18	1200	0.15	900	0.13	1750	0.18
8.0	1200	0.20	900	0.18	680	0.15	1300	0.20
10.0	960	0.22	720	0.20	550	0.18	1100	0.22
12.0	800	0.24	600	0.22	450	0.20	880	0.24
15.0	630	0.28	480	0.24	350	0.22	700	0.28
20.0	470	0.33	360	0.26	260	0.24	530	0.33
25.0	380	0.36	290	0.28	210	0.26	420	0.36
30.0	310	0.40	240	0.30	180	0.28	330	0.40

Workpiece Material	Stainless Steel				Copper Alloys, Brass		Aluminium Alloys	
	Martensitic Ferritic AISI 430		Austenitic AISI 304 Precipitation-Hardening ASTM 630					
Dia. DC (mm)	Revolution (min ⁻¹)	Feed rate (mm/rev)	Revolution (min ⁻¹)	Feed rate (mm/rev)	Revolution (min ⁻¹)	Feed rate (mm/rev)	Revolution (min ⁻¹)	Feed rate (mm/rev)
0.5	8000	0.01	6000	0.01	8000	0.01	10000	0.02
1.0	5000	0.02	4000	0.02	6000	0.02	7000	0.04
2.0	2500	0.05	2300	0.04	4700	0.05	6000	0.08
3.0	1900	0.10	1500	0.07	3200	0.10	5500	0.13
6.0	950	0.18	750	0.10	1600	0.18	3100	0.23
8.0	700	0.20	530	0.13	1200	0.20	2300	0.28
10.0	560	0.22	420	0.15	960	0.22	1900	0.33
12.0	460	0.24	340	0.17	800	0.24	1600	0.38
15.0	360	0.26	270	0.20	630	0.26	1300	0.42
20.0	270	0.28	200	0.23	470	0.28	950	0.45
25.0	210	0.32	160	0.24	380	0.32	750	0.48
30.0	180	0.35	135	0.25	310	0.35	630	0.50

Note 1) Please reduce the cutting conditions when drilling deep holes.

Note 2) This table only shows standard cutting conditions with water-soluble cutting fluids. Please make corrections or adjustments depending on the application.

Reduction rate of cutting conditions for hole drilling

Drilling Depth	Reduction Rate of Cutting Speed	Reduction Rate of Feed	Drilling Depth	Reduction Rate of Cutting Speed	Reduction Rate of Feed
4DC	10%	10%	8DC	30%	20%
5DC	10%	15%	10DC	30%	25%
6DC	20%	20%	15DC	40%	30%
7DC	20%	20%	20DC	40%	45%

DC : Drill dia.