

Identification(Shoulder Milling)

Reduce the cutting parameters by the coefficient values shown according to the length of overhang.
For long edge and oversize types heads refer to their specific recommended conditions.

(inch)

L/D	Carbon Steels, Alloy Steels, Mild Steels, Copper, Copper Alloys			Pre-hardened Steels, Carbon Steels, Alloy Steels, Alloy Tool Steels			Austenitic Stainless Steels, Ferritic and Martensitic Stainless Steels, Titanium Alloys		
	Revolution n (min ⁻¹)	Feed per Tooth fz (IPT)	Width of Cut ae	Revolution n (min ⁻¹)	Feed per Tooth fz (IPT)	Width of Cut ae	Revolution n (min ⁻¹)	Feed per Tooth fz (IPT)	Width of Cut ae
2	100%	100%	100%	100%	100%	100%	100%	100%	100%
3	100%	100%	100%	100%	100%	100%	100%	100%	100%
4	80%	90%	70%	80%	90%	70%	80%	90%	70%
5	60%	80%	40%	60%	80%	40%	60%	80%	40%
6	50%	70%	30%	50%	70%	30%	50%	70%	30%
7	40%	70%	20%	40%	70%	20%	30%	60%	20%
8	40%	60%	10%	40%	60%	10%	30%	50%	10%
9	30%	60%	10%	30%	60%	10%	20%	50%	10%

L/D	Precipitation Hardening Stainless Steels, Cobalt Chromium Alloys			Heat Resistant Alloys Inconel718		
	Revolution n (min ⁻¹)	Feed per Tooth fz (IPT)	Width of Cut ae	Revolution n (min ⁻¹)	Feed per Tooth fz (IPT)	Width of Cut ae
2	100%	100%	100%	100%	100%	100%
3	100%	100%	100%	100%	100%	100%
4	80%	90%	70%	80%	90%	70%
5	60%	80%	40%	60%	80%	40%
6	50%	70%	30%	50%	70%	30%
7	30%	60%	20%	30%	60%	20%
8	30%	50%	10%	30%	50%	10%
9	20%	50%	10%	20%	50%	10%


iMX-C6HV/C10HV/C12HV


Corner radius head, Multi-flute, Irregular helix

Recommended Cutting Conditions

Shoulder Milling

(inch)

Workpiece Material		Pre-hardened Steels, Carbon Steels, Alloy Steels, Alloy Tool Steels				Austenitic Stainless Steels, Ferritic and Martensitic Stainless Steels, Titanium Alloys				Precipitation Hardening Stainless Steels, Cobalt Chromium Alloys			
		Revolution n (min ⁻¹)	Feed Rate vf (IPM)	Depth of Cut ap	Width of Cut ae	Revolution n (min ⁻¹)	Feed Rate vf (IPM)	Depth of Cut ap	Width of Cut ae	Revolution n (min ⁻¹)	Feed Rate vf (IPM)	Depth of Cut ap	Width of Cut ae
DC													
(mm)	(inch)												
	.3750	6700	112.6	.375	.038	5000	84.0	.375	.038	3400	57.1	.375	.038
10	.3937	6400	107.5	.394	.039	4800	80.6	.394	.039	3200	53.8	.394	.039
12	.4724	5300	104.9	.472	.047	4000	79.2	.472	.047	2700	53.5	.472	.047
	.5000	5000	99.0	.500	.050	3700	73.3	.500	.050	2500	49.5	.500	.050
	.6250	4000	140.0	.625	.025	3000	105.0	.625	.025	2000	70.0	.625	.025
16	.6299	4000	140.0	.630	.025	3000	105.0	.630	.025	2000	70.0	.630	.025
	.7500	3300	154.4	.750	.030	2500	117.0	.750	.030	1700	79.6	.750	.030
20	.7874	3200	149.8	.787	.031	2400	112.3	.787	.031	1600	74.9	.787	.031
25	.9843	2500	117.0	.984	.039	1900	88.9	.984	.039	1300	60.8	.984	.039
	1.0000	2500	117.0	1.000	.040	1900	88.9	1.000	.040	1300	60.8	1.000	.040
Depth of Cut													

Workpiece Material		Heat Resistant Alloys Inconel718			
		Revolution n (min ⁻¹)	Feed Rate vf (IPM)	Depth of Cut ap	Width of Cut ae
DC					
(mm)	(inch)				
	.3750	1300	10.1	.375	.019
10	.3937	1300	10.1	.394	.020
12	.4724	1100	9.2	.472	.024
	.5000	990	8.3	.500	.025
	.6250	790	11.9	.625	.025
16	.6299	790	11.9	.630	.025
	.7500	660	12.7	.750	.030
20	.7874	630	12.1	.787	.031
25	.9843	500	9.6	.984	.039
	1.0000	500	9.6	1.000	.040
Depth of Cut					

- Note 1) The irregular helix flute end mill has a larger effect on controlling vibration when compared to standard end mills. However, if the rigidity of the machine or the workpiece material installation is poor, vibration or abnormal sound can occur. In this case, please reduce the revolution and the feed rate proportionately, or set a lower depth of cut.
- Note 2) If the depth of cut is smaller, the revolution and the feed rate can be increased.
- Note 3) If the machining radius at the corner is the same as the tool radius when using a head with more than 10 flutes, please set the depth of cut and feed rate to half of the above.
- Note 4) For stainless steels, titanium alloys and heat resistant alloys, the use of water-soluble coolant is effective.

