

Recommended Cutting Conditions

Work Material	Properties	Cutting Mode	Chip Breaker		Recom- mendation	Cutting Speed (m/min)	L/D ≤ 3 (Steel shank)		L/D ≤ 4-5 (Steel shank)		
							Feed (mm/rev)	Depth of Cut (mm)	Feed (mm/rev)	Depth of Cut (mm)	
P Mild Steel	≤180HB	Finish	FP	FV	NX2525	170 (120-220)	0.10 (0.05-0.15)	-0.5	0.10 (0.05-0.15)	-0.5	
			LP	SV	MP3025	150 (100-200)	0.20 (0.10-0.25)	-1.0	0.15 (0.05-0.20)	-1.0	
		Light	LP	SV	NX2525	160 (110-210)	0.20 (0.10-0.25)	-1.0	0.15 (0.05-0.20)	-1.0	
			SV	-	NX3035	150 (100-200)	0.20 (0.10-0.25)	-1.0	0.15 (0.05-0.20)	-1.0	
		Medium	MP	MV	MP3025	140 (90-190)	0.25 (0.15-0.35)	-2.0	0.20 (0.15-0.25)	-1.5	
			MV	-	NX3035	140 (90-190)	0.25 (0.15-0.35)	-2.0	0.20 (0.15-0.25)	-1.5	
	Carbon Steel Alloy Steel	180-350HB	Finish	FP	-	MC6015	140 (90-190)	0.10 (0.05-0.15)	-0.5	0.10 (0.05-0.15)	-0.5
				FV	-	VP15TF	140 (90-190)	0.10 (0.05-0.15)	-0.5	0.10 (0.05-0.15)	-0.5
			Light	FP	FV	NX2525	130 (80-180)	0.10 (0.05-0.15)	-0.5	0.10 (0.05-0.15)	-0.5
				LP	SV	MC6025	140 (90-190)	0.20 (0.10-0.25)	-1.0	0.15 (0.05-0.20)	-1.0
			Medium	LP	SV	MP3025	110 (60-160)	0.20 (0.10-0.25)	-1.0	0.15 (0.05-0.20)	-1.0
				SV	-	NX3035	110 (60-160)	0.20 (0.10-0.25)	-1.0	0.15 (0.05-0.20)	-1.0
M Stainless Steel	≤200HB	Finish	MP	MV	MC6025	130 (80-180)	0.25 (0.15-0.35)	-2.0	0.20 (0.15-0.25)	-1.5	
			MP	MV	MP3025	100 (60-150)	0.25 (0.15-0.35)	-2.0	0.20 (0.15-0.25)	-1.5	
		Light	MV	-	NX3035	100 (60-150)	0.25 (0.15-0.35)	-2.0	0.20 (0.15-0.25)	-1.5	
			FM	FV	VP15TF	150 (110-190)	0.10 (0.05-0.15)	-0.5	0.10 (0.05-0.15)	-0.5	
		Medium	LM	-	MC7025	125 (85-165)	0.20 (0.10-0.25)	-1.0	0.15 (0.05-0.20)	-1.0	
			SV	-	US735	125 (85-165)	0.20 (0.10-0.25)	-1.0	0.15 (0.05-0.20)	-1.0	
K Gray Cast Iron	Tensile Strength ≤350MPa	Finish	LM	SV	VP15TF	130 (90-170)	0.20 (0.10-0.25)	-1.0	0.15 (0.05-0.20)	-1.0	
			MM	-	MC7025	105 (70-135)	0.20 (0.10-0.25)	-2.0	0.20 (0.15-0.25)	-1.0	
		Medium	MV	-	US735	125 (85-165)	0.20 (0.10-0.25)	-1.0	0.15 (0.05-0.20)	-1.0	
			MM	MV	VP15TF	120 (80-160)	0.20 (0.10-0.25)	-2.0	0.20 (0.15-0.25)	-1.0	
		Finish	F	FS	HTi10	130 (90-160)	0.15 (0.10-0.20)	-0.5	0.15 (0.05-0.20)	-0.5	
			MK	-	MC5015	90 (60-120)	0.20 (0.15-0.25)	-2.0	0.20 (0.15-0.25)	-1.5	
N Aluminium Alloy	-	Finish	MV	-	VP15TF	90 (60-120)	0.20 (0.10-0.25)	-2.0	0.20 (0.15-0.25)	-1.5	
			Chip	FS	HTi10	300 (200-400)	0.10 (0.05-0.15)	-0.5	0.10 (0.05-0.15)	-0.5	
H Hardened Steel	35-65HRC	Finish	Flat Top	-	MD220	200 (150-250)	0.10 (0.05-0.15)	-2.0	0.10 (0.05-0.15)	-1.0	
			Flat Top	-	MB8120	100 (80-200)	0.10 (0.05-0.15)	-0.15	0.10 (0.05-0.15)	-0.1	

Note 1) When vibrations occur, reduce cutting speed by 30%.

Note 2) The depth of cut needs to be less than the corner diameter when using the FSVJ type.

Note 3) The recommended pressure for the internal coolant is 1MPa.