

RECOMMENDED CUTTING CONDITIONS

	Workpiece Material	Grade	Cutting Speed (m/min)	Feed (mm/rev)	Depth of Cut (mm)
N	Aluminium Alloy	HTi10	400	0.05—0.3	0.2—3.0
		MD220	800	0.05—0.3	0.2—0.5