



RECOMMENDED CUTTING CONDITIONS

Work material			Cemented carbide				Alumina Zirconia			
DC (mm)	RE (mm)	LU (mm)	Revolution (min ⁻¹)	Feed rate (mm/min)	Depth of cut ap (mm)	Depth of cut ae (mm)	Revolution (min ⁻¹)	Feed rate (mm/min)	Depth of cut ap (mm)	Depth of cut ae (mm)
0.2	0.1	0.5	30000	30	0.005	0.01	30000	30	0.005	0.01
0.4	0.2	1	30000	100	0.015	0.08	30000	100	0.015	0.08
0.6	0.3	1.5	30000	200	0.03	0.14	30000	200	0.03	0.14
0.8	0.4	2	30000	250	0.04	0.19	30000	250	0.04	0.19
1	0.5	2.5	30000	300	0.05	0.25	30000	300	0.05	0.25
1	0.5	5	30000	300	0.05	0.25	30000	300	0.05	0.25
1.5	0.75	3.8	30000	300	0.075	0.275	30000	300	0.075	0.275
2	1	6	30000	300	0.1	0.3	30000	300	0.1	0.3
2	1	10	30000	300	0.1	0.3	30000	300	0.1	0.3
3	1.5	8	27500	275	0.125	0.33	27500	275	0.125	0.33
4	2	10	24000	240	0.15	0.35	24000	240	0.15	0.35
5	2.5	10	22000	220	0.175	0.37	22000	220	0.175	0.37
6	3	10	20000	200	0.2	0.4	20000	200	0.2	0.4



Work material			Silicon carbide Silicon nitride				Quartz glass			
DC (mm)	RE (mm)	LU (mm)	Revolution (min ⁻¹)	Feed rate (mm/min)	Depth of cut ap (mm)	Depth of cut ae (mm)	Revolution (min ⁻¹)	Feed rate (mm/min)	Depth of cut ap (mm)	Depth of cut ae (mm)
0.2	0.1	0.5	30000	15	0.003	0.005	30000	45	0.008	0.015
0.4	0.2	1	30000	50	0.008	0.04	30000	150	0.023	0.12
0.6	0.3	1.5	30000	100	0.015	0.07	30000	300	0.045	0.21
0.8	0.4	2	30000	125	0.02	0.095	30000	375	0.06	0.285
1	0.5	2.5	30000	150	0.025	0.125	30000	450	0.075	0.375
1	0.5	5	30000	150	0.025	0.125	30000	450	0.075	0.375
1.5	0.75	3.8	30000	150	0.038	0.138	30000	450	0.113	0.413
2	1	6	30000	150	0.05	0.15	30000	450	0.15	0.45
2	1	10	30000	150	0.05	0.15	30000	450	0.15	0.45
3	1.5	8	27500	138	0.063	0.165	27500	413	0.188	0.495
4	2	10	24000	120	0.075	0.175	24000	360	0.225	0.525
5	2.5	10	22000	110	0.088	0.185	22000	330	0.263	0.555
6	3	10	20000	100	0.1	0.2	20000	300	0.3	0.6



- 1) The cemented carbide in the above mentioned cutting conditions table is based on CIS standard VM-40(90HRA).
- 2) Air blow or dry processing is recommended with cemented carbide processing.
*Note: Using coolants or oil mists may decrease tool longevity.
- 3) The use of a water soluble cutting oil is recommended with the processing of hard brittle materials other than the cemented carbide mentioned in the above table. Be sure to refuel the oil and eliminate any chip discharge that adheres to the tool.
- 4) Cutting conditions may need adjustments depending on the type of work material.
- 5) Reduce the rotation speed and feedrate shown in the above table at a similar ratio when no rigidity in the machinery or work mounting and occurrence of chatter or abnormal sound.
- 6) Implementation of special countermeasures is recommended since fine chip discharge may enter gaps in the processing machinery.