


RECOMMENDED CUTTING CONDITIONS


High depth of cut conditions

(mm)

Workpiece Material		Carbon steel, Alloy steel, Gray cast iron						Pre-hardened steel, Alloy tool steel						Hardened steel (45—55HRC)					
		AISI 1045, AISI 4140, AISI No 45 B						AISI P21, AISI P20, SKD, SKT						AISI H13, AISI L6					
Dia. DC	Corner R RE	Cutting Speed (m/min)	Revolution (min ⁻¹)	Feed per Tooth (mm/t)	Feed rate (mm/min)	Depth of cut ap	Width of Cut ae	Cutting Speed (m/min)	Revolution (min ⁻¹)	Feed per Tooth (mm/t)	Feed rate (mm/min)	Depth of cut ap	Width of Cut ae	Cutting Speed (m/min)	Revolution (min ⁻¹)	Feed per Tooth (mm/t)	Feed rate (mm/min)	Depth of cut ap	Width of Cut ae
10	2	90	2900	0.25	2900	1.2	4.5	75	2400	0.23	2200	1	4.5	60	1900	0.22	1700	0.7	4.5
12	2	90	2400	0.25	2400	1.8	6	75	2000	0.23	1800	1.4	6	60	1600	0.22	1400	0.9	6
16	3	90	1800	0.25	1800	1.8	7.5	75	1500	0.23	1400	1.4	7.5	60	1200	0.22	1100	0.9	7.5
20	3	90	1400	0.25	1400	1.8	9	75	1200	0.23	1100	1.4	9	60	950	0.22	840	0.9	9
25	4	90	1100	0.25	1100	2.4	11.5	75	950	0.23	870	1.8	11.5	60	760	0.22	670	1.2	11.5
Depth of cut																			

High-speed milling

(mm)

Workpiece Material		Carbon steel, Alloy steel, Gray cast iron						Pre-hardened steel, Alloy tool steel						Hardened steel (45—55HRC)					
		AISI 1045, AISI 4140, AISI No 45 B						AISI P21, AISI P20, SKD, SKT						AISI H13, AISI L6					
Dia. DC	Corner R RE	Cutting Speed (m/min)	Revolution (min ⁻¹)	Feed per Tooth (mm/t)	Feed rate (mm/min)	Depth of cut ap	Width of Cut ae	Cutting Speed (m/min)	Revolution (min ⁻¹)	Feed per Tooth (mm/t)	Feed rate (mm/min)	Depth of cut ap	Width of Cut ae	Cutting Speed (m/min)	Revolution (min ⁻¹)	Feed per Tooth (mm/t)	Feed rate (mm/min)	Depth of cut ap	Width of Cut ae
10	2	150	4800	0.4	7700	0.6	4.5	125	4000	0.35	5600	0.46	4.5	100	3200	0.3	3800	0.36	4.5
12	2	150	4000	0.45	7200	0.9	6	125	3300	0.4	5300	0.7	6	100	2700	0.3	3200	0.45	6
16	3	150	3000	0.5	6000	0.9	7.5	125	2500	0.45	4500	0.7	7.5	100	2000	0.3	2400	0.45	7.5
20	3	150	2400	0.5	4800	0.9	9	125	2000	0.45	3600	0.7	9	100	1600	0.35	2200	0.45	9
25	4	150	1900	0.5	3800	1.2	11.5	125	1600	0.45	2900	0.9	11.5	100	1300	0.35	1800	0.6	11.5
Depth of cut																			

Note 1) If the depth of cut is shallow, the revolution and feed rate can be increased.

Note 2) Air blow or oil mist is recommended for good chip evacuation.

Note 3) For profile machining such as moulds, machining conditions may differ considerably depending on the workpiece geometry, machining methods and depth of cut. Reduce the feed rate especially when machining the corner sections of a workpiece.

Note 4) Vibration may occur if there is poor rigidity of the machine or workpiece material. In that case, please adjust the revolution, feed rate and depth of cut.