


RECOMMENDED CUTTING CONDITIONS

Work material		Hardened steel (45—55HRC)				Hardened steel (55—62HRC)			
		AISI H13 etc.				AISI D2 etc.			
RE (mm)	LU (mm)	Revolution (min ⁻¹)	Table feed (mm/min) (IPM)		Depth of cut ap (mm)	Revolution (min ⁻¹)	Table feed (mm/min) (IPM)		Depth of cut ap (mm)
R 0.1	0.5	40000	300	11.8	0.003	40000	300	11.8	0.002
	1	40000	300	11.8	0.002	40000	300	11.8	0.002
	1.5	40000	300	11.8	0.001	40000	200	7.9	0.001
	2	40000	200	7.9	0.001	40000	100	3.9	0.001
	2.5	40000	100	3.9	0.001	40000	60	2.4	0.001
R 0.15	1	40000	500	19.7	0.007	40000	500	19.7	0.005
	1.5	40000	500	19.7	0.005	40000	500	19.7	0.003
	2	40000	500	19.7	0.003	40000	500	19.7	0.002
	2.5	40000	400	15.7	0.003	40000	400	15.7	0.002
	3	40000	300	11.8	0.002	40000	300	11.8	0.001
R 0.2	4	30000	200	7.9	0.002	30000	200	7.9	0.001
	1	40000	1400	55.1	0.015	40000	1400	55.1	0.01
	1.5	40000	1000	39.4	0.01	40000	1000	39.4	0.006
	2	40000	1000	39.4	0.01	40000	1000	39.4	0.006
	2.5	40000	700	27.6	0.005	40000	700	27.6	0.003
	3	40000	700	27.6	0.005	40000	700	27.6	0.003
R 0.25	4	40000	600	23.6	0.004	40000	500	19.7	0.003
	5	40000	400	15.7	0.003	40000	300	11.8	0.002
	1.5	40000	2000	78.7	0.02	40000	2000	78.7	0.015
	2	40000	2000	78.7	0.02	40000	2000	78.7	0.015
	3	40000	1200	47.2	0.015	40000	1200	47.2	0.01
	4	36000	900	35.4	0.01	36000	900	35.4	0.007
R 0.3	5	36000	700	27.6	0.007	36000	600	23.6	0.005
	6	36000	600	23.6	0.006	36000	500	19.7	0.004
	2	40000	2800	110.2	0.03	40000	2800	110.2	0.02
	3	40000	2800	110.2	0.03	40000	2800	110.2	0.02
	4	35000	2000	78.7	0.02	35000	2000	78.7	0.015
	5	30000	1000	39.4	0.01	30000	1000	39.4	0.007
	6	30000	800	31.5	0.008	30000	800	31.5	0.005
	7	30000	600	23.6	0.008	30000	600	23.6	0.005
R 0.4	8	25000	400	15.7	0.006	25000	400	15.7	0.004
	2	40000	3500	137.8	0.04	40000	3500	137.8	0.03
	3	40000	3000	118.1	0.04	40000	3000	118.1	0.03
	4	40000	3000	118.1	0.02	40000	3000	118.1	0.015
	6	30000	1600	63.0	0.02	30000	1600	63.0	0.01
	8	25000	1000	39.4	0.01	25000	1000	39.4	0.007
R 0.5	10	25000	600	23.6	0.008	25000	600	23.6	0.005
	3	40000	4000	157.5	0.05	40000	4000	157.5	0.04
	4	40000	4000	157.5	0.05	40000	4000	157.5	0.04
	5	40000	3000	118.1	0.03	40000	3000	118.1	0.02
	6	35000	2000	78.7	0.03	35000	2000	78.7	0.02
	8	30000	1600	63.0	0.02	30000	1600	63.0	0.01
	10	20000	1000	39.4	0.01	20000	1000	39.4	0.01
	12	20000	1000	39.4	0.01	18000	800	31.5	0.008
	14	18000	600	23.6	0.008	18000	480	18.9	0.008
	16	18000	500	19.7	0.008	18000	400	15.7	0.006
R 0.6	18	13000	300	11.8	0.005	13000	240	9.4	0.004
	20	13000	250	9.8	0.005	13000	200	7.9	0.004
	6	40000	4000	157.5	0.05	35000	3500	137.8	0.04
	8	40000	3000	118.1	0.05	27000	2000	78.7	0.04
	10	27000	1900	74.8	0.03	24000	1700	66.9	0.02
	12	16000	1100	43.3	0.02	16000	1000	39.4	0.01
R 0.7	14	16000	850	33.5	0.01	16000	780	30.7	0.01
	16	15000	500	19.7	0.01	14000	400	15.7	0.006
	8	40000	4500	177.2	0.06	28000	3200	126.0	0.05
	12	32000	3000	118.1	0.03	19000	1800	70.9	0.02
	16	15000	1000	39.4	0.02	14000	800	31.5	0.01
R 0.75	16	15000	1200	47.2	0.03	13000	1200	47.2	0.02
	6	40000	5000	196.9	0.07	32000	4000	157.5	0.06
	8	40000	5000	196.9	0.07	28000	3500	137.8	0.06
	10	40000	4500	117.2	0.06	21000	2400	94.5	0.04
	12	32000	3400	133.9	0.04	19000	2000	78.7	0.03
	14	16000	1500	59.1	0.04	13000	1200	47.2	0.03



1) If the depth of cut is smaller than this table, feed rate can be increased.
 2) Cutting conditions may differ considerably due to the overhang, depth of cut, and machine tool conditions. Please use the above table as a start reference point.